

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>7</sup> :</b> <b>C08G 18/42, 18/66, 18/10</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 00/50485</b> <b>(43) International Publication Date:</b> 31 August 2000 (31.08.00)
<b>(21) International Application Number:</b> PCT/US00/04398 <b>(22) International Filing Date:</b> 22 February 2000 (22.02.00) <b>(30) Priority Data:</b> 60/121,292 23 February 1999 (23.02.99) US <b>(71) Applicant (for all designated States except US):</b> HUNTSMAN ICI CHEMICALS LLC [US/US]; 500 Huntsman Way, Salt Lake City, UT 84108 (US). <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> LIN, Nai, Wen [US/US]; 2200 N. Fairview Lane, Rochester Hills, MI 48306 (US). JOSHI, Ravi, R. [IN/US]; Apartment E, 31439 Mound Road, Warren, MI 48092 (US). <b>(74) Agent:</b> BOLAND, Kevin, J.; Huntsman Polyurethanes, 286 Mantua Grove Road, West Deptford, NJ 08066-1732 (US).		<b>(81) Designated States:</b> AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
<b>(54) Title:</b> POLYURETHANE ELASTOMERS HAVING IMPROVED HYDROLYSIS RESISTANCE		
<b>(57) Abstract</b>  The disclosed invention relates to a polyurethane elastomer that has improved hydrolysis resistance. The polyurethane elastomer is made by reacting a polyol blend of an aromatic dicarboxylic acid based polyester polyol, an aliphatic dicarboxylic acid based polyester polyol, and a blowing agent. The polyol blend is reacted with an isocyanate terminated prepolymer. The aromatic dicarboxylic acid based polyester polyol is the reaction product of an aliphatic alcohol and ortho-phthalic acid. The aliphatic dicarboxylic acid based polyester polyol is the reaction product of adipic acid and glycols.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

**TITLE OF THE INVENTION**

Polyurethane Elastomers Having Improved Hydrolysis Resistance

5

**TECHNICAL FIELD**

The invention relates to hydrolysis resistant polyester polyurethane elastomers. More particularly, the invention relates to polyurethane elastomers for use in footwear, especially shoe soles.

10

**BACKGROUND ART**

Polyester polyurethanes for applications such as footwear should have excellent flexural properties and hydrolysis resistance. Polyester polyurethane elastomers made with aromatic ester polyols such as o-phthalic acid polyester polyols have excellent hydrolysis resistance. However, these elastomers have poor flexural properties. Polyester polyurethanes made with aliphatic polyester polyols such as adipic acid polyester polyols have excellent flexibility, but poor hydrolysis resistance.

Polyester polyurethane elastomers made with aliphatic polyester polyols such as adipic acid based polyols have employed additives such as caprolactone polyols and carbodiimides such as Staboxyl I in an attempt to achieve improved properties. Caprolactone polyols, however, are undesirably expensive. Use of carbodiimides such as Staboxyl I do not produce polyester polyurethane elastomers which have satisfactory hydrolysis resistance as gauged by retained tensile strength after aging in humid environments.

Retained tensile strength of polyester polyurethanes made with aliphatic polyester polyols which include Staboxyl I is only about 60-70% of the original tensile strength after humid aging at 70°C and 100% relative

humidity for seven days. For applications wherein the polyester polyurethanes are employed as shoe soles, the retained tensile strength is desirably about 75-90% of the tensile strength prior to aging.

- 5       A need therefore exists for polyester polyurethane formulations which can be used to produce polyurethanes which show improved hydrolysis resistance and which avoid the disadvantages of the prior art.

10                               **DISCLOSURE OF THE INVENTION**

- The invention relates to polyurethanes having improved hydrolysis resistance and tensile strength retention. The polyurethanes are made by reacting an isocyanate terminated prepolymer with a polyol component  
15       which includes a polyester polyol blend made from an aliphatic carboxylic acid based polyester polyol, preferably adipic acid based polyester polyol, and an aromatic carboxylic acid based polyester polyol, preferably o-phthalic acid based polyester polyol.

- 20       More specifically, the polyurethane elastomers are made by reacting a first component comprising a polyol component having a blend of an aromatic dicarboxylic acid based polyester polyol, and an aliphatic dicarboxylic acid based polyester polyol, a blowing agent and  
25       preferably, a chain extender, with an isocyanate terminated prepolymer. The aromatic dicarboxylic acid based polyester polyol is the reaction product of an aliphatic alcohol and ortho-phthalic acid. The aliphatic alcohol is any of ethylene glycol, diethylene glycol,  
30       hexanediol, and neopentyldiol. The aliphatic dicarboxylic acid is any of adipic acid, succinic acid, glutaric acid, and suberic acid. The aromatic polyester polyol is present in the polyol blend in an amount of about 12 wt.% to about 26 wt.%, preferably about 15 wt.% to about 20

wt.%, based on the weight of the polyol blend, remainder aliphatic polyester polyol. In a preferred aspect, the ortho-phthalic acid reacted with the aliphatic alcohol has less than about 10 wt. % total of tere-phthalic acid and isophthalic acid.

The aliphatic dicarboxylic acid based polyester polyol is the reaction product of adipic acid and glycol or glycols such as ethylene glycol, diethylene glycol, and 1,4-butanediol, and has an OH value of about 36 to about 56. The blowing agent is any of water, acetone, pentane, hexane, cyclopentane, (1,1,1,2-tetrafluoroethane), (1,1,1,3,3-pentafluoropropane), (1,1,2,2,3-pentafluoropropane), (1,1,1,2,3,3-hexafluoropropane), and methylene chloride, preferably water in an amount of about 0.02% to about 1.2% by weight based on the total weight of the polyol component.

In a more preferred aspect, the polyurethane elastomers of the invention are the reaction products of a first component comprising a polyol component that includes a polyol blend formed of an aliphatic polyester polyol and an aromatic polyester polyol, with a second component that is a diphenylmethane diisocyanate prepolymer having about 15% NCO to about 24% NCO. The aliphatic polyester polyol is the reaction product of adipic acid with diethylene glycol and ethylene glycol. The aromatic polyester polyol is the reaction product of diethylene glycol with ortho-phthalic acid. The aromatic polyester polyol is present in an amount of about 15 wt.% to about 20 wt.% of the polyol blend, remainder aliphatic polyester polyol. The polyol component also includes 1,4 butanediol as a chain extender and water as a blowing agent.

Having summarized the invention, the invention is

described in detail below by reference to the following detailed description and non-limiting examples.

5

**MODES FOR CARRYING OUT THE INVENTION****Glossary:**

The following trade name materials and terms have the meanings given below:

- 10                   1.    Dabco S25 from Air Products Co. is triethylene diamine in 1,4-butanediol.
2.    Daltorez P716 from Huntsman Polyurethanes, Inc. is an ethylene glycol/diethylene glycol/adipic acid polyester polyol having a functionality of 2.0, and OHv = 56.
- 15                   3.    Daltorez P720 from Huntsman Polyurethanes, Inc. is a polyester polyol made of Ethylene glycol/1,4-butane diol/adipic acid, Fn=2, OHv=55
- 20                   4.    Daltorez P778 from Huntsman Polyurethanes, Inc. is a ethylene glycol/diethylene glycol/adipic acid polyester polyol having a functionality of 2.0, a MW of 2500, and a OHv=45.
- 25                   5.    Daltorez P779 from Huntsman Polyurethanes, Inc. is an ethylene glycol/diethylene glycol/adipic acid polyester polyol having a functionality of 2.0 and OHv = 37.
- 30                   6.    Daltoped AP 17108 is a polyester polyol blend from Huntsman Polyurethanes, Inc.;
- 35                   7.    Daltoped HF 54615 is a polyester polyol blend available from Huntsman Polyurethanes, Inc.. Daltoped HF 54615 includes 86.5% Daltorez P716, 9.6% 1,4-Butanediol, 2.8% Dabco S-25, 0.47% Niox DEOA-LF, 0.3% DC-193 and 0.33% water.
- 40                   8.    DC-193 is a silicone surfactant from Air Products Co.
- 45

- 5 9. Formrez 8009-146 from Witco Co. is an isophthalic acid polyester polyol having a functionality of 2.0 and a  $\text{OH}_v=146$ .
- 10 10. Niox DEOA-LF is diethanol amine from Union Carbide Co.
- 15 11. Staboxyl I from Rhien Chemie is bis 2,2',6,6' tetra isopropyl-diphenyl carbodiimide.
- 20 12. Rubinate 1680 is a uretonimine modified MDI from Huntsman Polyurethanes, Inc.
- 25 13. Rubinate 9044 is diphenylmethane diisocyanate from Huntsman Polyurethanes, Inc.
- 30 14. Rubinol F 481 is a polyether polyol made from EO/PO, EO capped,  $\text{OH}_v=30$  diol from Huntsman Polyurethanes, Inc.
- 35 15. Stepanpol PS 1752 from Stepan Co. is diethylene glycol-orthophthalic anhydride based polyester polyol having a MW of 640, a functionality of 2.0 and an hydroxyl number of 160-180 mg KOH/gm.
- 40 16. Stepanpol PS-3152 from Stepan Co. is a diethylene glycol-phthalic anhydride based polyester polyol a diethylene glycol-phthalic anhydride based polyester polyol having a functionality of 2.0, a MW of 356, and an hydroxyl number of 300-330 mg KOH/gm.
- 45 17. Stepanpol PD-110LV from Stepan Co. is a diethylene glycol/ortho-phthalate based polyester polyol having a functionality of 2.0, a MW of 975, and an hydroxyl number of 110-120 mg KOH/gm.
- 50 18. Stepanpol PH-56 from Stepan Co. is a ortho phthalate-1,6-hexanediol polyester polyol having a functionality of 2.0, and an hydroxyl number of 53-59 mg KOH/gm.
19. Stepanpol PN-110 from Stepan Co. is an ortho phthalate-neopentyl glycol polyester polyol having a functionality of 2.0, and

an hydroxyl number of 110-120 mg KOH/gm.

- 5                   20.   Stepanpol PS 20-200A from Stepan Co. is an orthophthalate-diethylene glycol polymer polyol having hydroxyl number of 190-200, and a functionality of 2.0.
- 10                   21.   Stepanpol PS 2002 from Stepan Co. is an orthophthalate diethylene glycol polyester polyol having hydroxyl number of 200, and a functionality of 2.0.
- 15                   22.   Suprasec 2000 from Huntsman Polyurethanes is a diphenylmethane diisocyanate prepolymer that is the reaction product of a polyester polyol and diphenylmethane diisocyanate, and having a 17% NCO. The polyester polyol is the reaction product of a blend of ethylene glycol/diethylene glycol with adipic acid.
- 20                   23.   Suprasec 2433 from Huntsman Polyurethanes is a diphenylmethane diisocyanate prepolymer that is the reaction product of polyether polyol and diphenylmethane diisocyanate, and having 18.7 to 19.3% NCO. The polyether polyol is EO/PO and EO capped diol.
- 25                   24.   Suprasec 2544 from Huntsman Polyurethanes is an diphenylmethane diisocyanate prepolymer having 19% NCO. It is the reaction product of Rubinate 9044, Rubinol F 481, Daltorez P720, and Rubinate 1680.
- 30                   25.   Molecular weight, unless otherwise specified, is number average.
- 35

40           In the present invention, a polyol component formed from a blend of an aromatic polyester polyol and an aliphatic polyester polyol is reacted with an isocyanate prepolymer to produce a polyurethane having greatly improved hydrolysis resistance. The polyol component

45           includes suitable catalysts, blowing agents, and optionally, chain extenders and additives.

Aromatic polyester polyols for use in the polyol



component may be prepared by polycondensation of aromatic dicarboxylic acids or dicarboxylic acid derivatives, for example aromatic dicarboxylic acid anhydrides or aromatic diesters, with aliphatic diols and/or triols. Suitable aromatic dicarboxylic acids are terephthalic acid and ortho-phthalic acid, preferably, ortho-phthalic acid. More preferably, the aromatic dicarboxylic acid is ortho-phthalic acid that has less than about 10% of terephthalic acid and isophthalic acid. Other suitable aromatic acids which may be used to prepare the prepolymer include mixtures of the ortho-phthalic acid with fatty acid dimers such as C18 fatty acid dimers.

Aliphatic diols and triols which may be used to prepare the aromatic polyester polyols are, for example: ethanediol, diethylene glycol, 1,4 -butanediol, neopentyl glycol, 1,6 hexanediol, 1,3- and 1,2-propanediol, dipropylene glycol, triethylene glycol, tetraethylene glycol, glycerin, trimethylolpropane and triethylolpropane, preferably diethylene glycol.

The aromatic polyester polyols are prepared from any of tere-phthalic acid, isophthalic acid, ortho-phthalic acid or mixtures thereof and ethylene glycol and/or diethylene glycol. More preferably, the aromatic polyester polyols are prepared from ortho-phthalic acid and ethylene glycol and/or diethylene glycol. Preferably, the aromatic polyester polyol is formed from ortho-phthalic acid having a molecular weight of about 256 to about 3000, preferably about 344 to about 1500, more preferably about 640.

The aromatic polyester polyols which may be used have molecular weights of from about 256 to about 3000, preferably from about 344 to about 1500, and functionalities of 2 to 3, preferably 2. These aromatic

polyols have acid numbers less than 3, more preferably about 0.2 to 0.8, and hydroxyl numbers from about 37 to about 438, preferably about 75 to about 315.

Examples of commercially available aromatic

5 polyester polyols for use in the invention include Stepanpol PS-3152, Stepanpol PS 20-200A, Stepanpol PS 2002, Stepanpol PS 1752, Stepanpol PD-110 LV, Stepanpol PH-56, and Stepanpol PN-110, preferably Stepanpol PS 1752.

10 Aliphatic polyester polyols which may be used can be prepared, for example, from organic dicarboxylic acids having from 2 to 12 carbon atoms, preferably aliphatic dicarboxylic acids having from 4 to 6 carbon atoms, more preferably 6 carbon atoms, and polyfunctional alcohols,  
15 preferably diols having from 2 to 12 carbon atoms, more preferably from 2 to 4 carbon atoms. Typical dicarboxylic acids are: succinic acid, glutaric acid, adipic acid, and suberic acid, preferably adipic acid. The dicarboxylic acids may be used individually or in mixtures with one  
20 another. preferably, adipic acid is used alone. Instead of the free dicarboxylic acids, corresponding dicarboxylic acid derivatives may be used, for example dicarboxylic acid esters of alcohols having from 1 to 4 carbon atoms, or dicarboxylic anhydrides.

25 Examples of di- and polyfunctional alcohols which may be used, in particular, diols, are: ethanediol, diethylene glycol, 1,2- and 1,3-propanediol, dipropylene glycol, 1,4-butanediol, 1,5-pentanediol, 1,6-hexanediol, 1,10-decanediol, preferably diethylene glycol. Examples  
30 of triols are glycerin and trimethylolpropane, preferably used are ethylene glycol and diethylene glycol. The polyester polyols preferably have a functionality of from 2 to 3 and a molecular weight of from 1000 to 3000, more preferably from 1800 to 2500, and functionality of from

2.0 to 2.2.

Examples of commercially available aliphatic polyester polyols for use in the invention include Daltorez P716, Daltorez P778, Daltorez P779, and Daltorez  
5 P778, preferably Daltorez P778.

The aromatic polyester polyol and the aliphatic polyester polyol may be blended in weight ratios of aromatic polyester polyol:aliphatic polyester polyol of about 13:87 to about 28.7:71.3, preferably about  
10 16.6:83.4 to about 22:78. The aromatic polyester polyol preferably is Stepanpol PS 1752 and the aliphatic polyester polyol is Daltorez P778, and the weight ratio of Stepanpol PS 1752 to Daltorez P778 is about 13:87 to about 28.7:71.3, preferably about 16.6:83.4 to about  
15 22:78.

Suitable catalysts for use in the polyol component include, tertiary amine catalysts and organometallic catalysts. Some examples of organometallic catalysts include, organometallic compounds of lead, iron, bismuth,  
20 and mercury.

Examples of amine catalysts include trialkyl amines and heterocyclic amines. Suitable compounds include, for example, trimethylamine, triethylamine, tripropylamine, tributylamine, dimethylcyclohexylamine,  
25 dibutylcyclohexylamine, dimethylethanolamine, triethanolamine, diethylethanolamine, ethyldiethanolamine, dimethylisopropanolamine, triisopropanolamine, triethylene diamine, tetramethyl-1,3-butanediamine, N,N,N',N'-tetramethylethylenediamine,  
30 N,N,N',N'-tetramethylhexanediamine-1,6, N,N,N',N',N"-pentamethyl diethylenetriamine, bis(2-dimethylaminoethoxy)-methane, N,N,N'-trimethyl-N'-(2-hydroxyethylethyldiamine, N,N-dimethyl-N',N'-(2-hydroxyethyl)-ethylenediamine, tetramethylguanidine,

-methylpiperidine, N-ethylpiperidine, -methyldmorpholine, N-ethyldmorpholine, 1,4-dimethylpiperidine, 1,2,4-trimethylpiperidine, -(2-dimethylaminoethyl)-morpholine. Examples of commercially available catalysts for use in  
5 the polyol component include Dabco S25, and Niox DEOA-LF.

The amine catalysts are usually used in amounts ranging from about 0.1 to about 1.5% by weight, preferably about 0.3% to about 1.1% by weight, based on the total weight of the polyol component.

10 At least one blowing agent is included in the polyol component. Suitable blowing agents include, for example, water, and physical blowing agents. Useful physical blowing agents include low boiling alkanes, partially or completely fluorinated hydrocarbons, etc. Suitable low  
15 boiling alkanes include compounds such as, for example, acetone, pentane, hexane, cyclopentane, etc. Some examples of suitable partially or completely fluorinated hydrocarbons include compounds such as HFC-134a (1,1,1,2-tetrafluoroethane), HFC-245fa (1,1,1,3,3-  
20 pentafluoropropane), HFC-245ca (1,1,2,2,3-pentafluoropropane), HFC-236ca (1,1,1,2,3,3-hexafluoropropane). Methylene chloride is also a suitable blowing agent for the presently claimed invention. Mixtures of these various blowing agents are also  
25 suitable. It is preferred that the blowing agent comprises water.

When water is used as the sole blowing agent, it is typically used in amounts of between about 0.02% to about 1.2% by weight, and preferably between about 0.05% to  
30 about 0.7% by weight based on the total weight of the polyol component side of the formulation. In the present invention, blowing agents are added in an amount necessary to produce a foam of the desired density for use as, for example, shoe soles. In shoe soles, the  
35 density of the molded foam is usually from about 0.2 to about 1.2 g/cc, preferably 0.4 to about 1.1 g/cc.

Normally, densities can be as high as about 1 g/cc to about 1.1 g/cc when used in dual-density shoe soles where a higher density out-sole is attached to a lower-density mid-sole. Chain extenders optionally are most

5 preferably included in the polyol blend. Chain extenders include glycerols and diols which have at least 2 hydroxyl groups and a MW less than about 300. Examples of useful chain extenders are glycerols and diols which have primary hydroxyl groups, glycerols and diols which have  
10 secondary hydroxyl groups, and glycerols and diols which have both primary and secondary hydroxyl groups. preferably, the chain extenders are diols which have primary hydroxyl groups and a molecular weight of more than about 62. Examples of these chain extenders include  
15 but are not limited to ethylene glycol, diethylene glycol, 1,4 butane diol, 2,3 butanediol, and 1,2 propane diol, preferably 1,4 butane diol and ethylene glycol.

Various additives may be included in the polyol component. Examples of suitable additives include  
20 surface-active additives such as emulsifiers and foam stabilizers. Examples include N-stearyl-N',N'-bis-hydroxyethyl urea, oleyl polyoxyethylene amide, stearyl diethanol amide, isostearyl diethanolamide, polyoxyethylene glycol monoleate, a  
25 pentaerythritol/adipic acid/oleic acid ester, a hydroxy ethyl imidazole derivative of oleic acid, N-stearyl propylene diamine and the sodium salts of castor oil sulfonates or of fatty acids. Alkali metal or ammonium salts of sulfonic acid such as dodecyl benzene sulfonic  
30 acid or dinaphthyl methane sulfonic acid and also fatty acids may be used as surface-active additives. Other additives which may be used in the molding compositions of the present invention include known internal mold release agents, pigments, cell regulators, flame  
35 retarding agents, plasticizers, dyes, fillers and reinforcing agents such as glass in the form of powder

and antistatic agents. Examples of fillers include calcium carbonate, talc, magnesium hydroxide, mica, clay, barium sulfate, natural silica, synthetic silica (white carbon), titanium oxide, and carbon black. Among those,  
5 barium sulphate and synthetic silica are preferred.

Foam stabilizers which also optionally may be employed include water-soluble polyether siloxanes. The structure of these compounds is generally that of a copolymer of ethylene oxide and propylene oxide attached  
10 to a polydimethyl siloxane. A preferred foam stabilizer is the silicone surfactant available from Air Products Co. under the tradename DC-193.

Isocyanate prepolymers are employed in preparation of the foams of the present invention. The prepolymer  
15 preferably has an NCO value of about 15 to about 26%, more preferably about 16-21%, and a functionality of 2.0 to 2.5, more preferably from 2.0 to 2.1.

Isocyanate terminated prepolymers can be formed by a variety of methods known in the art. Suitable  
20 isocyanate-terminated prepolymers can be prepared by reacting an excess of polymeric or di-isocyanate with polyols, including aminated polyols, imine- or enamine-modified polyols, polyether polyols, polyester polyols or polyamines. The prepolymer then can be mixed with one or  
25 more additives such as MDI derivatives, plasticizers and stabilizers. One or more chain extenders also may be used to replace the polyol (or a portion of polyols) to make the prepolymer.

Examples of suitable prepolymers for use in the invention include prepolymers formed from Stepanpol PS  
30 1752 and MDI, aromatic polyols such as Bisphenol A, and aliphatic polyols. Examples of commercially available prepolymers which may be used in the invention include Suprasec 2000, Suprasec 2544, Suprasec 2980, and Suprasec  
35 2433.

**Manufacture of Polyester Polyurethanes**

The B side (polyol component) and A-side (isocyanate prepolymer) can be reacted at indices of about 92 to about 106, preferably about 96 to about 100, most  
5 preferably about 98 to produce polyester polyurethanes. During manufacture of the polyester polyurethanes, additives, if employed, are incorporated into the "B" side component, although they may be added into the "A" side component provided that they are not isocyanate-  
10 reactive.

The components included in the "B" side, including additives, may be blended or agitated in a container or supply tank at a temperature of of about 20°C to about 75°C, preferably about 20°C to about 50°C. Agitation can  
15 be performed with conventional propeller type stirrers at about 50 to about 200 RPM.

Examples of specific B-side formulations and isocyanates are shown in Table 1. In Table 1, Example 1 is conventional shoe sole formulation in which the only  
20 polyol is the commercially available aliphatic polyester polyol Daltorez P778. Example 2 is similar to Example 1 but includes 1% Staboxyl I, carbodiimide. Examples 3 and 4 employ o-phthalic ester polyols such as Stepanpol PS 1752 with aliphatic ester polyols such as Daltorez P778  
25 and Daltorez P 716. All amounts shown in Table 1 are in wt. % based on the total weight of the B-side.

TABLE 1				
Example/Component	Example 1	Example 2	Example 3	Example 4
Dabco S 25	4.39	4.39	4.00	2.8
Daltorez P716	—	—	—	70.6
Daltorez P 778	90.58	90.58	74.00	—
DC-193	—	—	—	0.30
Niax DEOA-LF	—	—	—	0.47
Staboxyl I	—	1.00	—	—
Stepanpol PS1752	—	—	16.6	15.9
Water	0.05	0.05	0.05	0.33
1,4 butanediol	4.98	4.98	5.00	9.6
Isocyanate Prepolymer	Suprasec 2000	Suprasec 2000	Suprasec 2000	Suprasec 2000
Index	98	98	98	98

#### Manufacture of Molded polyester polyurethanes

In manufacture of molded polyester polyurethanes, the "A" side and "B" side components are placed in separate containers equipped with agitators. The temperature of each component can vary from ambient to about 70°C.

Molded shoe soles are made by supplying each of the "A" and "B" side components via metering pumps to a mixing head where they are mixed at pressures of up to about 30 bar, preferably of up to about 20 bar. During mixing, the temperature of the B side is about 40 °C and the temperature of the A side is about 35 °C. The resulting mixture of A and B components is poured or injected into a mold.

After the mold is filled, the mold is closed and the



mixture is cured at about 30°C to about 60°C for about 1 to 30 minutes, preferably at about 45 °C to about 55 °C for about 2 to 10 minutes.

5           Molded shoe soles also can be formed as dual density shoe soles. Dual density shoe soles are made by a two-step injection method. In the first step, the mixture of A-side and B-side components is injected into a dual density mold cavity such as a Caroline Boots dual density shoe mold from Amtrial, Inc.. The dual density mold cavity includes closed mold cavity that is surrounded by an upper mold, a bottom mold and side rings to produce a thin outsole elastomer. When the outsole elastomer is cured in the mold, the upper mold is removed to provide space for making a midsole. The shoe upper is present as a part of an outer mold.

10           In the second step, another mixture of A-side and B-side components is injected into the mold between the shoe upper and the outsole to produce a midsole foam between the outsole and the shoe upper. The outsole and shoe upper then are glued together.

15           The polyester polyurethanes produced as described above are evaluated for flexural strength, tensile strength, and tensile strength after aging in a humid environment. The flexural strength of the polyester polyurethanes are evaluated according to the Ross Flexural test described in ASTM-D-1052-85. In the Ross Flexural test, polyester polyurethane sheets which measure 6" x 1" x 1/4" are used. The sheets are formed with a 0.08 inch crack and are repeatedly bent over a 25 mm diameter mandrel. Sheets which survive 50 kilo cycles (KCS) of bending at room temperature and 40 kilo cycles at -15°C are acceptable.

20           The tensile strength after aging in humid environments of the polyester polyurethanes are evaluated

in accordance with ASTM D 412-92. Sheets of polyester polyurethanes which measure 6" x 1" x 1/8" are used in ASTM D 412-92. Retention of tensile strength is calculated from the tensile strength before and after  
5 humid aging at 70°C, 100% relative humidity for seven days. The results are shown in Table 2.

The flexural strength of dual density shoe soles which utilize polyester polyurethanes is evaluated according to the Bata Belt Test described in SATRA Test  
10 method PM 133 published by the SATRA Technology Center, UK. Shoe soles which survive 35-50 kilo cycles of bending are considered as low risk for fatigue cracking and are acceptable. The results are shown in Table 2.

17

Table 2

Sample No.	Composition of Sample	Tensile Strength Before Aging, PSI	Tensile Strength After Aging, PSI	Tensile Strength Retention, %	Ross Flex, RT, -15C KCS	Bata Belt Flex, KCS	Index	Density, g/cc
1	Example 1	2924	718	24.6	50 50	50	96	1.0-1.1
2	Example 1	3278	907	27.7	50 50	45	98	1.0-1.1
3	Example 1	3302	1223	37.0	50 50	40	100	1.0-1.1
4	Example 2	3325	1830	55.0	50 50	50	96	1.0-1.1
5	Example 2	3001	2151	71.7	50 45	45	98	1.0-1.1
6	Example 2	3296	2123	64.4	50 40	40	100	1.0-1.1
7	Example 3	2548	1633	64.1	50 50	50	96	1.0-1.1
8	Example 3	2825	2627	93.0	50 50	45	98	1.0-1.1
9	Example 3	2903	2592	89.3	50 45	40	100	1.0-1.1
10	Example 4	880	908	102.7	50 50	50	96	0.45-0.55
11	Example 4	812	1008	124.1	50 50	50	98	0.45-0.55
12	Example 4	845	849	100.5	50 50	50	100	0.45-0.55

As shown in Table 2, samples 7-9 which employ the compositions of Example 3 retain as much as 93% of their original tensile strength. This exceeds the highest level of tensile strength retention achievable with prior art compositions which employ aliphatic polyester polyols which include Staboxyl I carbodiimide.

To further illustrate the invention, modified o-phthalate ester polyols are evaluated for use with adipic acid based polyester polyols at various indices.

Prepolymers formed from the modified polyols are also evaluate. These modified polyols are referred to as P 1752M and P 3152M. The prepolymer is referred to as S 2000M. The compositions evaluated are shown in Table 3.

P 1752M is made using Stepanpol PS 1752 and adipic acid in the weight ratio of Stepanpol PS 1752/adipic acid of 44/56. P 1752M is made by charging Stepanpol PS 1752 to a reactor and then heating it until the temperature of the polyol reaches 115 °C. Adipic acid is added and the temperature of the reactor is raised to 150 °C with agitation. A partial vacuum of 20 inches Hg is maintained and the temperature is maintained below 230 °C, preferably about 200 °C to about 220 °C. When the acid number of the reaction mixture is less than 2 as determined by titration, a vacuum of less than two inches Hg is applied until the reaction mixture achieves an OH<sub>v</sub> of 72-78.

P 3152M, having a MW of 1450, is made in accordance with the following two step procedure. In step 1, Stepanpol SP 3152 is reacted with adipic acid at the weight ratio of Stepanpol SP 3152:adipic acid of 1:2 to achieve an acid terminated intermediate. Stepanpol SP 3152 is added to the reactor and heated to 115 °C. Adipic acid is added to the reactor and the temperature raised to 150 °C with agitation and under a partial vacuum of 20 inches Hg. The reaction is continued for 2 hours while

maintaining the temperature below 230 °C, preferably about 200 °C to about 220 °C. The resulting acid terminated intermediate then is cooled to 115 °C use in step 2.

- 5 In step 2, the acid terminated intermediate is reacted with ethylene glycol at the molar ratio of acid terminated intermediate:ethylene glycol of 2:3. Ethylene glycol is charged to the reactor having the acid terminated intermediate that is at 115 °C with agitation.
- 10 The temperature is raised to 150 °C under a partial vacuum of 20 inches Hg. The reaction is continued for two hours and the temperature is maintained below 230 °C, preferably about 200 °C to about 220 °C. When the acid number of the reaction mixture is less than 2 as
- 15 determined by titration, a vacuum of less than two inches Hg is applied until a OHv of 72-78 is achieved.

Table 3

Sample	Daltorez P778, PBW	P 3152 M, PBW	P 1752 M, PBW	Isocyanate	Index
13	56	34.6	0	S2000 <sup>1</sup>	96
14	56	34.6	0	S2000	98
15	56	34.6	0	S2000	100
16	40.6	50	0	S2000	96
17	40.6	50	0	S2000	98
18	40.6	50	0	S2000	100
19	52.9	0	37.7	S2000	96
20	52.9	0	37.7	S2000	98
21	52.9	0	37.7	S2000	100
22	37.7	0	52.9	S2000	96
23	37.7	0	52.9	S2000	98
24	37.7	0	52.9	S2000	100

1. Suprasec 2000

Table 4					
Sample	Tensile w/o aging, PSI	Tensile w/ 7 days Aging <sup>1</sup> , PSI	Tensile Retention .%	Ross Flex @-15C. KCs	Bata Belt Flex. ,KCs
13	2428	1648	67.9	45	50
14	2507	1886	75.2	45	50
15	2641	1866	67.9	35	45
16	1910	1617	84.7	35	50
17	2401	1840	76.6	25	20
18	3066	1788	58.3	25	35
19	2433	1502	61.7	25	50
20	2344	1775	75.7	25	30
21	2951	1706	57.8	40	50
22	2341	1487	63.5	30	30
23	2424	1701	70.2	10	20
24	2484	1704	68.6	10	15

The polyester polyurethanes prepared have excellent  
 5 hydrolysis resistance and mechanical characteristics,  
 including abrasion resistance, durability, stability and  
 flexibility, making them ideal for use as a shoe sole.

## Claims:

1. A polyurethane elastomer having improved hydrolysis resistance comprising the reaction product of  
a first component comprising a polyol blend having  
5 an aliphatic dicarboxylic acid based polyester polyol,  
an aromatic dicarboxylic acid based polyester polyol,  
chain extender and a blowing agent, and  
10 a second component having an isocyanate terminated prepolymer, wherein in the first component,  
the aromatic dicarboxylic acid based polyester polyol is the reaction product of an aliphatic alcohol and ortho-phthalic acid, and wherein the aromatic  
15 dicarboxylic acid based polyol is present in the polyol blend in an amount of about 12 wt.% to about 27 wt.% based on the weight of the polyol blend.
2. The polyurethane elastomer of claim 1 wherein the  
20 aliphatic alcohol is selected from the group consisting of ethylene glycol, diethylene glycol, hexanediol, 1,4 butanediol, neopentyldiol, and mixtures thereof.
3. The polyurethane elastomer of claim 1 wherein the  
25 aliphatic dicarboxylic acid is selected from the group consisting of adipic acid, succinic acid, glutaric acid, and suberic acid.
4. The polyurethane elastomer of claim 2 wherein the  
30 amount of aromatic dicarboxylic acid polyester polyol is about 14 wt.% to about 27 wt.% of the polyol blend.
5. The polyurethane elastomer of claim 1 wherein the  
35 isocyanate terminated prepolymer having about 17% NCO that is the reaction product of diphenylmethane

diisocyanate and a polyester polyol that is the reaction product of a blend of ethylene glycol/diethylene glycol with adipic acid.

- 5     6. The polyurethane elastomer of claim 5 wherein the aliphatic dicarboxylic acid based polyester polyol is the reaction product of adipic acid and a mixture including diethylene glycol and ethylene glycol.
- 10    7. The polyurethane elastomer of claim 6 wherein the aliphatic dicarboxylic acid based polyester polyol has an OH value of about 36 to about 56.
- 15     8. The polyurethane elastomer of claim 1 wherein the blowing agent is selected from the group consisting of water, acetone, pentane, hexane, cyclopentane, (1,1,1,2-tetrafluoroethane), (1,1,1,3,3-pentafluoropropane), (1,1,2,2,3-pentafluoropropane), (1,1,1,2,3,3-hexafluoropropane), and methylene chloride.
- 20     9. The polyurethane elastomer of claim 8 wherein the blowing agent is water.
- 25     10. The polyurethane elastomer of claim 8 wherein the blowing agent is water in an amount of about 0.02% to about 1.2% by weight based on the total weight of the polyol component.
- 30     11. The polyurethane elastomer of claim 1 wherein the isocyanate terminated prepolymer having about 18.7 %NCO to about 19.3% NCO that is the reaction product of diphenylmethane diisocyanate and a polyether polyol that is an EO/PO, EO capped diol.
- 35     12. The polyurethane elastomer of claim 1 wherein the



isocyanate terminated prepolymer has an NCO content of about 19% and is the reaction product of diphenylmethane diisocyanate, uretonimine modified diphenylmethane diisocyanate, polyester polyol and polyether polyol.

5

13. The polyurethane elastomer of claim 12 wherein polyester polyol is the reaction product of ethylene glycol, 1,4 butane diol, and adipic acid, and the polyether polyol is ethylene oxide capped diol.

10

14. The polyurethane elastomer of claim 1 wherein the chain extender is selected from the group consisting of ethylene glycol, diethylene glycol and 1,4 butanediol.

15. A polyurethane elastomer having improved hydrolysis resistance comprising the reaction product of

a first component comprising a polyol blend having an ortho-phthalic acid based polyester polyol formed as the reaction product of diethylene glycol with ortho-phthalic acid, the ortho-phthalic acid being substantially free of each of tere-phthalic acid and isophthalic acid, the ortho-phthalic acid being about 15 wt.% to about 20 wt.% of the polyol blend,

an adipic acid based polyester polyol formed as the reaction product of adipic acid and a mixture of ethylene glycol diethylene glycol, and

water as a blowing agent, and

a second component that is a diphenylmethane diisocyanate prepolymer having about 15% to about 24% NCO.

30

16. The polyurethane elastomer of claim 15 wherein the aromatic polyester polyol is the reaction product of a diethylene glycol-orthophthalic anhydride based polyester polyol and adipic acid in the weight ratio of the polyester polyol to the adipic acid of 44/56.

35

17. The polyurethane elastomer of claim 15 wherein the aromatic polyester polyol is the reaction product of an acid terminated intermediate with ethylene glycol at the molar ratio of acid terminated intermediate:ethylene glycol of 2:3, wherein the acid terminated intermediate is the reaction product of a diethylene glycol-phthalic anhydride based polyester polyol and adipic acid of a weight ratio of the diethylene glycol-phthalic anhydride based polyester polyol to the adipic acid of 1:2

## INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/04398

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08G18/42 C08G18/66 C08G18/10

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

WPI Data, EPO-Internal, PAJ

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 795 572 A (KA0) 17 September 1997 (1997-09-17) page 2, line 39 -page 3, line 49; claims 1-7; examples page 6, line 49 -page 7, line 32 -----	1-3
A	EP 0 013 461 A (AKZ0) 23 July 1980 (1980-07-23) page 6, line 9 -page 11, line 26; claims 1,9-18; example 4 -----	1
A	US 5 840 782 A (LIMERKENS ET AL) 24 November 1998 (1998-11-24) column 1, line 36 -column 4, line 26; claims -----	1

☐ Further documents are listed in the continuation of box C.

Patent family members are listed in annex.

## \* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&amp;" document member of the same patent family

Date of the actual completion of the international search

7 July 2000

Date of mailing of the international search report

14/07/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Bourgonje, A

# INTERNATIONAL SEARCH REPORT

information on patent family members

Inter. onal Application No

PCT/US 00/04398

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 795572 A	17-09-1997	CN 1166502 A	03-12-1997
		JP 9302065 A	25-11-1997
		US 5821554 A	13-10-1998
EP 13461 A	23-07-1980	NL 7900022 A	07-07-1980
		DE 2965166 D	11-05-1983
		JP 55092723 A	14-07-1980
US 5840782 A	24-11-1998	EP 0582385 A	09-02-1994
		AU 4191193 A	10-02-1994
		BR 9303246 A	08-03-1994
		CA 2101625 A	06-02-1994
		CN 1083821 A	16-03-1994
		DE 69307800 D	13-03-1997
		DE 69307800 T	28-05-1997
		DK 582385 T	11-08-1997
		ES 2096865 T	16-03-1997
		JP 6206967 A	26-07-1994
		MX 9304711 A	28-02-1994